Property Data

Envalior
Imagine the Future

# Durethan® P24 MB2

## PA6

*Compounding, Nonwoven Extrusion, Low Viscosity, no Additives*

Print Date: 2026-04-09

### Sustainability

Bio-based
Mass balanced

| PROPERTIES | TYPICAL DATA | UNIT | TEST METHOD |
|---|---|---|---|
| **GENERAL PROPERTIES** | DRY / COND | | |
| Viscosity number (sulfuric acid, 96%, 5 g/L) | 121 | ml/g | EN ISO 307 |
| Relative solution viscosity (sulfuric acid, 96%, 5 g/L) | 2.3 | | EN ISO 307 |
| Humidity absorption | 3 / * | % | Sim. to ISO 62 |
| Water absorption | 10 / * | % | Sim. to ISO 62 |
| Melting temperature (10°C/min) | 220 / * | °C | ISO 11357-1/-3 |
| Density | 1140 / - | kg/m³ | ISO 1183 |
| Shape of granules | spherical | | |

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.
Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.
Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.
Copyright © Envalior 2026. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

2026-04-15 10:45:00 Distributed by Mito polimeri