Makrolon® GF9417

Glass fiber (Normal fiber) reinforced grades / 10 % Glass fiber reinforced	polycarbonate; MVR (300 °C/1.2 kg) 6.0 cm³/10 min; 10 % glass fiber reinforced; flame retardant; UL 94V-0/1.5 mm and 5VA/3.0 mm; high viscosity; UV stabilized; easy release; injection molding - melt temperature 300°C; available in opaque colors only
ISO Shortname	PC-GF10 FR

	Property	Test Condition	Unit	Standard	typical Value
Rheological properties					
C	Melt volume-flow rate	300 °C/ 1.2 kg	cm³/10 min	ISO 1133	6
	Melt viscosity	1000 s^{-1}/ 300 °C	Pa·s	b.o. ISO 11443-A	320
C	Molding shrinkage, parallel	60x60x2 mm³	%	ISO 294-4	0.6
C	Molding shrinkage, normal	60x60x2 mm³	%	ISO 294-4	0.45
Mechanical properties (23 °C/50 % r. h.)					
C	Tensile modulus	1 mm/min	MPa	ISO 527-1,-2	3800
	Yield stress	5 mm/min	MPa	ISO 527-1,-2	62
	Yield strain	5 mm/min	%	ISO 527-1,-2	4.8
	Nominal strain at break	5 mm/min	%	ISO 527-1,-2	10
C	Stress at break	5 mm/min	MPa	ISO 527-1,-2	45
C	Strain at break	5 mm/min	%	ISO 527-1,-2	15
C	Charpy impact strength	23 °C	kJ/m²	ISO 179/1eU	150C
C	Puncture impact properties - maximum force	23 °C	N	ISO 6603-2	3900
C	Puncture impact properties - maximum force	-30 °C	N	ISO 6603-2	3700
C	Puncture energy	23 °C	J	ISO 6603-2	25
C	Puncture energy	-30 °C	J	ISO 6603-2	15
Thermal properties					
C	Temperature of deflection under load	1.80 MPa	°C	ISO 75-1,-2	137
C	Temperature of deflection under load	0.45 MPa	°C	ISO 75-1,-2	144
C	Vicat softening temperature	50 N; 50 °C/h	°C	ISO 306	144
C	Burning behavior UL 94 (1.5 mm) [UL recognition]		Class	UL 94	V-0
C	Burning behavior UL 94-5V [UL recognition]	3.0 mm	Class	UL 94	5VA
C	Oxygen index	Method A	%	ISO 4589-2	36
	Resistance to heat (ball pressure test)		°C	IEC 60695-10-2	130
	Relative temperature index (Tensile strength) [UL recognition]	1.5 mm	°C	UL 746B	125
	Relative temperature index (Tensile impact strength) [UL recognition]	1.5 mm	°C	UL 746B	125
	Relative temperature index (Electric strength) [UL recognition]	1.5 mm	°C	UL 746B	125
	Glow wire test (GWFI)	0.75 mm	°C	IEC 60695-2-12	960
	Glow wire test (GWFI)	1.5 mm	°C	IEC 60695-2-12	960
	Glow wire test (GWFI)	3.0 mm	°C	IEC 60695-2-12	960
	Glow wire test (GWIT)	0.75 mm	°C	IEC 60695-2-13	825
	Glow wire test (GWIT)	1.5 mm	°C	IEC 60695-2-13	850
	Glow wire test (GWIT)	3.0 mm	°C	IEC 60695-2-13	850
Electrical properties (23 °C/50 % r. h.)					
C	Volume resistivity		Ohm·m	IEC 62631-3-1	3E+14
C	Surface resistivity		Ohm	IEC 62631-3-2	8E+15
C	Electrical strength	1 mm	kV/mm	IEC 60243-1	37
C	Comparative tracking index CTI	Solution A	Rating	IEC 60112	175
Other properties (23 °C)					
C	Density		kg/m³	ISO 1183-1	1270
	Glass fiber content	Method A	%	b.o. ISO 3451-1	10
Processing conditions for test specimens					
C	Injection molding - Melt temperature		°C	ISO 294	300
C	Injection molding - Mold temperature		°C	ISO 294	110
C	Injection molding - Injection velocity		mm/s	ISO 294	200

2026-02-18 11:00:00 Distributed by Mito polimeri

Makrolon® GF9417

	Property	Test Condition	Unit	Standard	typical Value
Recommended processing and drying conditions					
	Melt temperatures		°C	-	280-320
	Standard Melt temperature		°C	-	300
	Mold Temperatures		°C	-	110
	Dry Air Drying Temperature		°C	-	120
	Dry Air Drying Time		h	-	2-3

C These property characteristics are taken from the CAMPUS plastics data bank and are based on the international catalogue of basic data for plastics according to ISO 10350.

Impact properties: N = non-break, P = partial break, C = complete break

2026-02-18 11:00:00 Distributed by Mito polimeri

Makrolon® GF9417

Disclaimer

Information Impact properties

Impact properties: N = non-break, P = partial break, C = complete break

Typical value

These values are typical values only. Unless explicitly agreed in written form, the do not constitute a binding material specification or warranted values. Values may be affected by the design of the mold/die, the processing conditions and coloring/pigmentation of the product. Unless specified to the contrary, the property values given have been established on standardized test specimens at room temperature.

General

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations are beyond our control. Therefore, it is imperative that you test our products, technical assistance, information and recommendations to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by Covestro. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent. With respect to health, safety and environment precautions, the relevant Material Safety Data Sheets (MSDS) and product labels must be observed prior to working with our products.

Non Medical and non Food Contact Grade

This product is not designated for the manufacture of a pharmaceutical/medicinal product, medical device or of intermediate products for medical devices1). This product is also not registered for Covestro for the use in other specifically regulated applications, in particular applications requiring regulatory registration, approval or notification (e.g. including cosmetics, plant protection, food processing, food contact and others). If the intended use of the product is for the manufacture of a pharmaceutical, medical device or of intermediate products for medical devices or for other specifically regulated applications which may lead to a regulatory obligation of Covestro, Covestro must be contacted in advance to provide its agreement to sell such product for such purpose. Nonetheless, any determination as to whether a product is appropriate for use in a pharmaceutical, medical device or intermediate products for medical devices or for the use in other specifically regulated applications, must be made solely by the purchaser of the product without relying upon any representations by Covestro, irrespective of the existence of any regulatory obligation for the registration, approval or notification. 1) Please see the "Guidance on Use of Covestro Products in a Medical Application" document.

Recommended Processing and Drying Conditions

Barrel temperatures are valid for a standard 3-zone barrel. Temperature set-up for different barrel types may change according to configuration. Values for hold pressure as percentage of injection pressure may vary depending on, amongst others, part geometry, injection molding machine and injection mold. Drying conditions are for dry air dryers only. Drying times and drying temperatures may differ depending on valid dryer type. Further information is provided by your local Covestro support as well as in the following brochures: Injection Molding of High Quality Molded Parts - Drying; Determining the Dryness of Makrolon by TVI Test; The fundamentals of shrinkage in thermoplastics; Shrinkage and deformation of glass fiber reinforced thermoplastics [...]. https://www.plastics.covestro.com/Library/Overview.aspx

Disclaimer shrinkage data

Shrinkage data is provided as a reference only, and is based on sample plaques molded under specific, controlled processing conditions. Shrinkage rates in production parts can vary and are influenced by several variables such as, but not limited to: part design (e.g. part size, thickness and geometry), mold design (e.g. gate type and location, runner design, mold materials, cooling system), molding conditions (e.g. processing temperature, mold temperature, packing time and pressure, injection speed). We suggest materials be evaluated in existing applicable molds to achieve the most accurate shrinkage estimation for your specific application and processing practices. The final choice of shrinkage is the responsibility of the user of the material, and should be made based on your experience and testing results. We shall not be liable for any damage caused by the use of the shrinkage data as provided by us. If you have any questions, pls consult technical representatives from Covestro.

Covestro AG

Kaiser-Wilhelm-Allee 60

51373 Leverkusen

Germany

www.solutions.covestro.com

2026-02-18 11:00:00 Distributed by Mito polimeri