Makrolon® IFR6555

Designation according to ISO 1043: PC FR

Product description

Polycarbonate; flame retardant; V-0 at 3.0 mm (UL 94); medium viscosity; easy release; available in transparent, translucent and opaque colors; no intentionally added PFAS

Applications

Injection molding; Electrical/electronic

Typical Values

Rheological properties

Property	Test Condition	Value	Unit	Standard
Melt Volume-flow Rate (MVR)	300 °C/1.2 kg	7	cm³/10 min	ISO 1133-1
Melt Viscosity	300 °C; 1,000 s^{-1}	230	Pa·s	b. o. ISO 11443-A

Mechanical properties (23 °C/50 % r. h.)

Property	Test Condition	Value	Unit	Standard
Tensile modulus	1 mm/min	2,350	MPa	ISO 527-1,-2
Yield Stress	50 mm/min	65	MPa	ISO 527-1,-2
Yield Strain	50 mm/min	6.1	%	ISO 527-1,-2
Nominal Strain at Break	50 mm/min	> 50	%	ISO 527-1,-2
Strain at Break	50 mm/min	85	%	ISO 527-1,-2
Stress at Break	50 mm/min	57	MPa	ISO 527-1,-2
Izod Notched Impact Strength	23 °C; 3 mm	50P	kJ/m²	ISO 21305/b. o. ISO 180/A

Impact properties: N = non-break, P = partial break, C = complete break

Thermal properties

Property	Test Condition	Value	Unit	Standard
Temperature of Deflection under Load	1.80 MPa	122	°C	ISO 75-1,-2
Temperature of Deflection under Load	0.45 MPa	137	°C	ISO 75-1,-2
Vicat Softening Temperature	50 N; 50 °C/h	143	°C	ISO 306
Vicat Softening Temperature	50 N; 120 °C/h	144	°C	ISO 306
Burning Behavior	3.0 mm	V-0		UL 94
Glow Wire Test (GWFI)	0.8 mm	900	°C	IEC 60695-2-12
Glow Wire Test (GWFI)	1.5 mm	900	°C	IEC 60695-2-12
Glow Wire Test (GWFI)	3.0 mm	960	°C	IEC 60695-2-12
Glow Wire Test (GWIT)	0.8 mm	850	°C	IEC 60695-2-13
Glow Wire Test (GWIT)	1.5 mm	850	°C	IEC 60695-2-13

2026-02-18 11:00:00 Distributed by Mito polimeri

Makrolon® IFR6555

Designation according to ISO 1043: PC FR

Property	Test Condition	Value	Unit	Standard
Glow Wire Test (GWIT)	3.0 mm	850	°C	IEC 60695-2-13

Electrical properties (23 °C/50 % r. h.)

Property	Test Condition	Value	Unit	Standard
Volume Resistivity		1E14	Ω·m	IEC 62631-3-1
Surface Resistivity		1E15	Ω	IEC 62631-3-2
Electric Strength	1 mm	32	kV/mm	IEC 60243-1
Comparative Tracking Index (CTI)	Solution A	175		IEC 60112

Other properties (23 °C)

Property	Test Condition	Value	Unit	Standard
Density		1,200	kg/m³	ISO 1183-1

Recommended processing and drying conditions

Property	Test Condition	Value	Unit	Standard
Melt Temperatures		280 - 320	°C	
Mold Temperatures		80 - 120	°C	
Dry Air Drying Temperature		120	°C	
Dry Air Drying Time		5	h	

Health and Safety Information

Before working with this product, you must read and become familiar with the available information on its risks, proper use, and handling. Information is available in several forms, e.g., in particular in the currently valid safety data sheets and product labels. For further information contact your Covestro representative.

The Product Safety First Program | Covestro

Please note that for products manufactured in different colors, safety data may vary depending on the color variant.

Disclaimer

General

The manner in which you use our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products to determine suitability for your processing and intended uses. Your analysis must at least include testing to determine suitability from a technical, health, safety, and environmental and regulatory standpoint. Such testing has not necessarily been done by Covestro, and Covestro has not obtained any approvals or licenses for a particular use or application of the product.

Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request.

2026-02-18 11:00:00 Distributed by Mito polimeri

Makrolon® IFR6555

Designation according to ISO 1043: PC FR

All information and including technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed by you that you assume and hereby expressly release indemnify us and hold us harmless from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.

Preliminary Datasheet

It is a product whose typical product properties have been determined on the basis of a limited statistic, which may lead to slightly different typical values in the future. Final statements about type conformity, processing capability, long-term testing under various conditions and statements about production and application parameters can therefore only be made to a limited extent.

Non Medical and non Food Contact
This product is not designated for the manufacture of a medical device or of intermediate products for medical devices (1). This product is also not designated for other specifically regulated applications (e.g. including cosmetics, plant protection, fertilisers, plant strengtheners, food processing, food contact and others). If the intended use of the product is for the manufacture of a medical device or of intermediate products for medical devices or for other specifically regulated applications Covestro must be contacted in advance to provide its agreement to sell such product for such purpose. Nonetheless, any determination as to whether a product is appropriate for use in a medical device or intermediate products for medical devices, for Food Contact products or cosmetic applications must be made solely by the purchaser of the product without relying upon any representations by Covestro.

1) Please see the Guidance on Use of Covestro Products in a Medical Application document.

Sample

Any samples provided by Covestro are for testing purposes only and not for commercial use.

Typical Value

These values are typical values only. Unless explicitly agreed in written form, they do not constitute a binding material specification or warranted values. Values may be affected by the design of the mold/die, the processing conditions and coloring/pigmentation of the product. Unless specified to the contrary, the property values given have been established on standardized test specimens at room temperature.

Recommended Processing and Drying Conditions

Barrel temperatures are valid for a standard 3-zone barrel. Temperature set-up for different barrel types may change according to configuration. Values for hold pressure as percentage of injection pressure may vary depending on, amongst others, part geometry, injection molding machine and injection mold. Drying conditions are for dry air dryers only. Drying times and drying temperatures may differ depending on valid dryer type.

Contact

Please use our contact form or contact us directly by sending an e-mail to technical-datasheets@cx.covestro.com .

2026-02-18 11:00:00 Distributed by Mito polimeri