Property Data

Envalior
Imagine the Future

# Pocan® BF4939

*Arnite® TV6 241 SN*

## PBT–GF20 FR(17)

*20% Glass Fiber Reinforced, Flame Retardant*

Print Date: 2026–04–09

| PROPERTIES | TYPICAL DATA | UNIT | TEST METHOD |
|---|---|---|---|
| **RHEOLOGICAL PROPERTIES** | **VALUE** | | |
| Molding shrinkage (normal) | 1.2 | % | ISO 294–4 |
| Molding shrinkage (parallel) | 0.6 | % | ISO 294–4 |
| **MECHANICAL PROPERTIES** | **VALUE** | | |
| Tensile modulus | 8500 | MPa | ISO 527–1/–2 |
| Stress at break | 120 | MPa | ISO 527–1/–2 |
| Strain at break | 2.5 | % | ISO 527–1/–2 |
| Charpy impact strength (+23°C) | 50 | kJ/m² | ISO 179/1eU |
| Charpy impact strength (–30°C) | 50 | kJ/m² | ISO 179/1eU |
| Charpy notched impact strength (+23°C) | 9 | kJ/m² | ISO 179/1eA |
| Charpy notched impact strength (–30°C) | 7 | kJ/m² | ISO 179/1eA |
| **THERMAL PROPERTIES** | **VALUE** | | |
| Melting temperature (10°C/min) | 225 | °C | ISO 11357–1/–3 |
| Temp. of deflection under load (1.80 MPa) | 210 | °C | ISO 75–1/–2 |
| Temp. of deflection under load (0.45 MPa) | 220 | °C | ISO 75–1/–2 |
| Coeff. of linear therm. expansion (parallel) | 0.4 | E–4/°C | ISO 11359–1/–2 |
| Coeff. of linear therm. expansion (normal) | 0.8 | E–4/°C | ISO 11359–1/–2 |
| Burning Behav. at 0.75 mm nom. thickn. | V–2 | class | IEC 60695–11–10 |
| Thickness tested | 0.75 | mm | IEC 60695–11–10 |
| Burning Behav. at 1.5 mm nom. thickn. | V–0 | class | IEC 60695–11–10 |
| Thickness tested | 1.5 | mm | IEC 60695–11–10 |
| Burning Behav. at 3.0 mm nom. thickn. | V–0 | class | IEC 60695–11–10 |

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.
Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.
Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.
Copyright © Envalior 2026. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

2026-04-15 10:45:00 Distributed by Mito polimeri

## Property Data

# Pocan® BF4939

*Arnite® TV6 241 SN*

Print Date: 2026–04–09

| PROPERTIES | TYPICAL DATA | UNIT | TEST METHOD |
|---|---|---|---|
| Thickness tested | 3 | mm | IEC 60695–11–10 |
| **ELECTRICAL PROPERTIES** | **VALUE** | | |
| Relative permittivity (100Hz) | 3.2 | – | IEC 62631–2–1 |
| Relative permittivity (1 MHz) | 3.2 | – | IEC 62631–2–1 |
| Dissipation factor (100 Hz) | 10 | E–4 | IEC 62631–2–1 |
| Dissipation factor (1 MHz) | 140 | E–4 | IEC 62631–2–1 |
| Volume resistivity | >1E13 | Ohm*m | IEC 62631–3–1 |
| Comparative tracking index | 250 | V | IEC 60112 |
| Comparative tracking index (PLC) | 2 | class | UL 746A |
| **OTHER PROPERTIES** | **VALUE** | | |
| Water absorption | 0.4 | % | Sim. to ISO 62 |
| Humidity absorption | 0.2 | % | Sim. to ISO 62 |
| Density | 1620 | kg/m³ | ISO 1183 |

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.
Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.
Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.
Copyright © Envalior 2026. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

2026-04-15 10:45:00 Distributed by Mito polimeri