Property Data

Envalior
Imagine the Future

Pocan® T7142 H50R3

Pocan® ECOT7142

(PET+PBT)–(GF+MX)40

40% Glass Fiber/Mineral Reinforced, Injection Molding, Recycled Content

Print Date: 2026–04–09

Sustainability

Mass balanced
Recycled based

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES	**VALUE**		
Molding shrinkage (normal)	0.8	%	ISO 294–4
Molding shrinkage (parallel)	0.2	%	ISO 294–4
MECHANICAL PROPERTIES	**VALUE**		
Tensile modulus	12000	MPa	ISO 527–1/–2
Stress at break	125	MPa	ISO 527–1/–2
Strain at break	1.6	%	ISO 527–1/–2
Flexural modulus	12000	MPa	ISO 178
Flexural strength	180	MPa	ISO 178
Flexural strain at flexural strength	1.8	%	ISO 178–A
Izod impact strength (+23°C)	35	kJ/m²	ISO 180/1U
THERMAL PROPERTIES	**VALUE**		
Melting temperature (10°C/min)	260	°C	ISO 11357–1/–3
Temp. of deflection under load (1.80 MPa)	205	°C	ISO 75–1/–2
Temp. of deflection under load (0.45 MPa)	250	°C	ISO 75–1/–2
Burning Behav. at 0.75 mm nom. thickn.	HB	class	IEC 60695–11–10
Thickness tested	0.75	mm	IEC 60695–11–10
Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695–11–10
Thickness tested	1.5	mm	IEC 60695–11–10

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.
Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.
Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.
Copyright © Envalior 2026. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

2026-04-15 10:45:00 Distributed by Mito polimeri

Property Data

Pocan® T7142 H50R3

Pocan® ECOT7142

Print Date: 2026–04–09

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Burning Behav. at 3.0 mm nom. thickn.	HB	class	IEC 60695–11–10
Thickness tested	3	mm	IEC 60695–11–10
Glow Wire Flammability Index GWFI	750	°C	IEC 60695–2–12
GWFI (Thickness (1) tested)	0.75	mm	IEC 60695–2–12
Glow Wire Flammability Index GWFI	750	°C	IEC 60695–2–12
GWFI (Thickness (2) tested)	1.5	mm	IEC 60695–2–12
Glow Wire Ignition Temperature GWIT	775	°C	IEC 60695–2–13
GWIT (Thickness (1) tested)	0.75	mm	IEC 60695–2–13
Glow Wire Ignition Temperature GWIT	775	°C	IEC 60695–2–13
GWIT (Thickness (2) tested)	1.5	mm	IEC 60695–2–13
Glow Wire Ignition Temperature GWIT	775	°C	IEC 60695–2–13
GWIT (Thickness (3) tested)	3	mm	IEC 60695–2–13

OTHER PROPERTIES	VALUE		
Density	1680	kg/m³	ISO 1183

PROCESSING RECOMMENDATIONS	VALUE		
Drying temperature circulating air dryer	120	°C	
Drying time circulating air dryer	4–8	h	
Residual moisture content	0.00–0.02	%	acc. to Karl Fischer
Melt temperature (Tmin – Tmax)	260–280	°C	
Mold temperature	80–100	°C	

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.
Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.
Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.
Copyright © Envalior 2026. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

2026-04-15 10:45:00 Distributed by Mito polimeri